



# GLORIA WALL PAINT



#### PACKAGING

3L / 9L / 15L



#### DRYING TIME

3-4 Hours



#### CONSUMPTION

6-7 m<sup>2</sup>/l

#### Description

GLORIA WALL PAINT is suitable for interior surfaces. It can be used for painting concrete cement, plain cement etc.

#### Surface Preparation

New surfaces made from marble plaster etc, must be primed with PN-301 primer diluted with water or PN-101. For old surfaces it must be ensured that all surfaces are clean free from dust and grease. Remove all poorly with abrasive paper No. 36 or No. 50 and prime the surface with PN-301 or PN-101 primer.

#### Application

Do not apply on very cold or damp surfaces, in humid conditions and in temperatures below 5°C (41°F). Apply easily with brush or roller. Apply two coats GLORIA WALL PAINT. Dilute the first coat with 15% water and after 2 - 4 hours apply the second coat diluted 10%. Prime the surface with PN-301 or PN-101 primer.

#### Coverage

GLORIA WALL PAINT cover 9-11 m<sup>2</sup>/L according to the surfaces.

#### Drying Time

Touch dry in 1 hour in good drying conditions and it can be recoated in 2-3 hours later.

#### After Painting

Clean equipment immediately with water and soap.

#### Package

3 L, 9 L and 15 L.



## TECHNICAL DATA (IN +23°C AND 50% U.R.)

Appearance	White water emulsion
Density (ISO2811, DIN 53217, ASTM D 1475)	1.58-1.62 g/cm <sup>3</sup>
Viscosity (RVDV -2T,R7)	4000-6500 cp
Solids Content (Termostat, 105°C/2orë)	≤ 70 %
Intermolecular forces (RVDV -2T,R7)	60000-120000 newton/m <sup>2</sup>
Kinematic viscosity (RVDV -2T,R7)	2400-4000 mm <sup>2</sup> /s
pH	≥8
Particle Size (Elcometer 2050, ISO 1524; ASTM D 1210)	10-40 μm